

Flexible PU Foam RAV3010M

Product composition:

The polymer composed of glycerin PO & EO

Quality specifications:

Appearance	Transparent liquid, without mechanical impurity
Colority (APHA)	≤50
Functionality	0.3
Hydroxyl value (mgKOH/g)	56±2
Average(Mol.Wt)	2900-3100
Acid value(mgKOH/g)	<0.05
Water content (%)	<0.05
K ⁺ ,Na ⁺ content,μg/g(ppm)	≤5
Unsaturation, mol/kg	≤0.03
Viscosity (25°C) mPa.s	500-750
PH value	6.0-7.5