

NYLON ENGINEERING PLASTICS

Properties	Unit	Test Method	RA0320GN
------------	------	-------------	----------

Mechanical

Tensile Str,Yield	Psi (Mpa)	D-638	14500
Tensile Elongation,Break	%	D-638	5.0
Flexural Strength	Psi (Mpa)	D-790	24500
Flexural Modulus	Psi (Mpa)	D-790	650000
Izod Impact Strength,Notched	ft.lb/in (J/m) 23°C -30°C	D-256	2.50 1.50
Rockwell Hardness	R-Scale	D-785	115

Thermal

Melting Point	°C	D-789	260
Heat Deflection Temperature	°C 66 Psi (0.45Mpa) °C 264 Psi(1.82Mpa)	D-648	- 240
Coefficient of Thermal Expansion	E-5 1/°C	D-696	-
Glow Wire Test	°C	IEC 695-2-1	-

Electrical

Dielectric Strength	kv/mm	D-149	-
Volume Resistivity	ohm-cm	D-257	-
Arc Resistance	sec	D-495	-

Other

Specific Gravity	-	D-792	1.20
Melt Flow Index	g/10 min (275°C / 5kg)	D-1238	-
Mold Shrinkage, Flow	% 3mm	D-955	30-70
Water Absorption	% 23°C,24hr	D-570	0.4-0.7

Flammability

Flammability	1/8" 1/16" 1/32"	UL-94	-
Remark	Polyamide 66, 15% Glass Fiber Reinforced Super Toughness Grade, Natural Color, RoHS Certification		